

CCF Decoupler Soft Foam

CCF Decoupler (Soft) Physical Properties	Target	Units	Test Method
Density	56–112	kg/m ³	ASTM D1056
	3.5–7.0	lbs/ft ³	
Compression Deflection, 25%	7 max.	kPa	ASTM D1056
	1 max.	psi	
Compression Set, 50% RT	10	%	ASTM D1056
Tensile	150	kPa	ASTM D1056
	22	psi	
Elongation	200	%	ASTM D1056
Water Absorption*	10 max.	%	ASTM D1056
Flammability, burn rate	102 max.	mm/min.	FMVSS 302
	4 max.	in./min.	
Temperature Use	148 / 300 (hot)	°C / °F	ASTM D1056
	-54 / -65 (cold)	°C / °F	
Gauge (skin two sides)	3 and above	mm	ASTM D1056
	0.118 and above	in.	

* Tested per 43.1 added skin clause

XX LSE and Low VOC Transfer Tape

A 3-mil quick initial tack, permanent, unsupported acrylic pressure sensitive film. XX has high peel and shear properties and is ideal for nameplates, automotive interior applications, and other demanding applications where a thin unsupported adhesive is preferred.

- Automotive Fogging Test: Passes SAE J1756 @ 100 °C as tested
- Odor: Passes SAE J 1351
- Low VOC as defined by the Japanese Ministry of Health, Labor & Welfare.
- Liner: 74# white poly-coated Kraft

Primary Use

XX is excellent for bonding to rigid and flexible plastics. Proven performance to a variety of low and high surface energy material including ABS, Powder Coated Paints, TPO, PE, PET and many other low surface energy materials.

Applications:

- Nameplates
- Automotive interior attachments
- Attaching to powder coated and other LSE finishes
- Cost effective option for many Low Surface Energy materials and applications
- Meets numerous automotive specifications

Typical Physical Properties¹

Thickness	3.0 mils (nominal)	5.5 mils (nominal)
Peel Adhesion ²		
PSTC #101; backed with 1 mil polyester 24 Hour Dwell	NA	58 oz/inch
PSTC #101; backed with 2 mil dead soft aluminum 24 Hour Dwell	NA	160 oz/inch
Shear Adhesion		
PSTC #107; Modified, 1000 gm/sq. in. @ 72 °F	NA	7+ Days no failure
PSTC #107; Modified, 500 gm/sq. in. @ 150 °F	NA	7+ Days no failure

¹ There is no industry wide accepted definition for Low VOC.

² Peel tests are performed as per PSTC #101, which states one-minute maximum dwell time. In general, for acrylic adhesives, longer residence time yields much higher peel values.

Physical Properties And Service¹

Loop Tack	PSTC #16; 125 oz/in
Service Temperature ²	-30 °F to 250 °F
Shelf Life	One year from date of shipment when stored under cool, dry conditions.

¹ The use of heat and pressure will help to increase the initial bond of the product to the substrate. Testing is recommended prior to laminating to any material that contains migrating plasticizers.

² This information is provided as a means to help characterize the adhesive's temperature resistance. Note that this data is based on limited testing and under no load. The practical service temperature of this or any adhesive system is dependent on many variables including the substrates being bonded, environmental conditions, and the loading and method of application. The purchaser is responsible for determining the suitability of this or any product for their particular purpose and process. The recommended application temperature is 68 °F to 100 °F.

The information contained herein is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation warranty, or guarantee is made regarding its accuracy, reliability, or completeness by ResoNix Sound Solutions, Inc. or any of its affiliates. It is the responsibility of the user to assure the suitability and completeness of such information and any depicted product for the particular use case of the user. ResoNix Sound Solutions, Inc. and its affiliates accept no liability for any loss or damage that may occur from the use of this information or any depicted product. ResoNix Sound Solutions, Inc. and its affiliates specifically and expressly disclaim any and all warranties, express or implied, including warranties of merchantability, fitness for a particular purpose, and freedom from claims of infringement of the rights of others associated with the sale or use of any product depicted. ResoNix Sound Solutions, Inc. and its affiliates further disclaim any liability for consequential or incidental damages of any kind, including lost profits.